

TECHNICAL DATA SHEET

Polyester TGIC yields highly decorative powder coatings suitable for application to product exposed to direct sunlight . This type of coating is applied to patio furniture, automotive trim, truck bodies, architectural extrusions, fire extinguishers, wire cloths, lawn and garden equipment, fencing and related items.

PRODUCT CODE:

PRODUCT TYPE: Polyester TGIC

PRODUCT NAME:

TYPICAL PROPERTIES

TEST METHODS

RESULTS

Specific Gravity	PCI # 4	1.2-1.8
Coverage	Theoretical	129 Sqft/lb @ 1 mil
Gloss @ 60 Degree	ASTM D523	0-90
Over Bake Resistance	ASTM D2454	Good
Pencil Hardness	ASTM D3363	H - 2H
Direct Impact	ASTM D2794	160 in lbs
Reverse Impact	ASTM D2794	160 in lbs
Cross Hatch, Adhesion	ASTM D3359B	Pass
Mandrel Bend, Flexibility	ASTM D522	1/4" no crack
Solvent Resistance	PCI # 8	50 + D/R
Abrasion Resistance	ASTM D968	Good
Salt Spray	ASTM B117	1000 Hrs
Humidity	ASTM D2247	1000 Hrs
UL DTOV2 Organic Coatings	Steel Enclosures, Elec Equip	Recognized

APPLICATION

Cure Schedule

Rec. Film Thickness

Electrostatic Spray:	Cold	10' @ 400 Degree F	2.0 to 3.0 mil
Substrate:	C.R.S.		
Pretreatment:	Bonderite 1000		

Note: All tests performed on Bonderite 1000 (Iron Phosphate) treated panels.

Shelf Life: 1 Year from the date of purchase, when stored under 75 degree F

Warranty Policy: All sales are subject to the AmeriCoats Standard Terms and Conditions then in effect, a copy of which can be found at [www.americoats.com/terms]. AmeriCoats will also provide a copy of the AmeriCoats Standard Terms and Conditions upon request. No additional or different terms or conditions will be binding upon AmeriCoats unless specifically agreed to in writing by an authorized representative. Please review all of the AmeriCoats Standard Terms and Conditions prior to entering any agreement with AmeriCoats. THE EXPRESS WARRANTY CONTAINED IN THE AMERICOATS STANDARD TERMS AND CONDITIONS IS EXCLUSIVE AND IN LIEU OF ALL OTHER REPRESENTATIONS AND WARRANTIES, EITHER EXPRESS OR IMPLIED, INCLUDING, WARRANTIES OF MERCHANTABILITY, NON-INFRINGEMENT, AND FITNESS FOR A PARTICULAR PURPOSE. The surface preparation and application procedures and other factors that affect performance are beyond our control. Do not use this product until the current material safety data sheet and technical data sheet have been read and fully understand. You must determine the suitability of this product for your own use and assume all risks and liabilities in connection therewith.